

# FINESSE 10.5 mm tongue/ groove

## Technical information:

<b>Produced according to:</b>	European parquet norm EN 13489 - 2002	
<b>Dimension:</b>	10.5 x 135 x 1350 mm	
<b>Toplayer:</b>	about 3.5 mm	
<b>Construction:</b>	2-layer construction; Hardwood top layer, Bottom layer made of spruce Top layer: approx. 3.5 mm Bottom layer: 7.0 mm	
<b>Boards/ m<sup>2</sup> per carton:</b>	14/ 2.55	
<b>Cartons/ m<sup>2</sup> per pallet:</b>	35/ 89.25	
<b>Divided strips per carton/ minimum length (mm):</b>	1/ 675	
<b>Weight per carton/ pallet in kg:</b>	15.00/ 525.00	
<b>Floor heating systems:</b>	Very well suitable	
<b>Fire behaviour <sup>1)</sup>:</b>	Cfl-s1 depending on wood species and surface treatment.	
<b>Content of formaldehyde <sup>2)</sup>:</b>	E1	
<b>Content of pentachlorophenol (PCP) <sup>2)</sup>:</b>	not detectable	
<b>Density kg/ m<sup>3</sup> <sup>2)</sup>:</b>	about 600	
<b>Antislip performance:</b>	Live Satin	USRV 25 <sup>2)</sup>
	Live Matt	USRV 43 <sup>2)</sup>
	Live Natural	USRV 74 <sup>2)</sup>
<b>Abrasion resistance:</b>	Live Satin	70/ 1100 <sup>3)</sup>
	Live Satin	100 <sup>4)</sup>
<b>Thermal conductivity <sup>2)</sup>:</b>	0.15 W/ mK	
<b>Areal thermal resistance <sup>5)</sup>:</b>	0.07 m <sup>2</sup> K/ W	



DOP 4658-1.1-07.2013



Emissionsgeprüftes  
Bauprodukt nach  
DIBT-Grundsätzen.

<sup>1)</sup> according to DIN EN 13501-1, <sup>2)</sup> according to DIN 14342, <sup>3)</sup> according to ENV 13696, <sup>4)</sup> according to DIN 68861, <sup>5)</sup> according to EN 12524