



# KINDA

Earth greys on a warm base, balanced contrast and transparency. Hard brushed, very rustic board with highlighted knots and cracks.

## PRODUCT DESCRIPTION

<b>Article Number</b>	151NDSEK02KW240
<b>Surface Treatment</b>	Oil
<b>Refining Treatment</b>	Bevelled 4-sided, handscraped, brushed, saw marks
<b>Dimensions</b>	2420 x 187 x 15 mm
<b>Weight per Package</b>	22 kg
<b>Area per Package</b>	2.72 m <sup>2</sup>
<b>Area Per Board</b>	0.453 m <sup>2</sup>

## DETAIL DESCRIPTION

All naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

## COLOUR CHANGE

The colour matures over time.

## FACTS

<b>Wood Species</b>	Oak
<b>Design</b>	1-strip
<b>Grading</b>	Expressive
<b>Range</b>	Kährs Supreme
<b>Collection</b>	Småland Collection
<b>Natural/Stained</b>	Stained
<b>Brinell Value</b>	3, 7
<b>Joint</b>	Woodloc® 5S
<b>Floor heating</b>	Yes
<b>Wear-layer material</b>	Hardwood
<b>Core material</b>	Pine/Spruce lamella
<b>Thickness</b>	15 mm
<b>Installation method</b>	Floating, glue-down
<b>EAN Code</b>	7393969039031
<b>Surface Colour</b>	Earth Grey

## CERTIFICATE



## TECHNICAL PROPERTIES

<b>Moisture content</b>	EN13183	7%±2%
<b>Minimum Mean Density kg/m<sup>3</sup></b>		>500 kg/m <sup>3</sup>
<b>Reaction To Fire</b>	EN13501-1	Dfl-s1
<b>Formaldehyde Emission</b>	EN717-1	E1
<b>Content PCP</b>	CEN/TR14823	≤ 5 x 10-6n
<b>Breaking Strength N/mm<sup>2</sup></b>	EN1533	NPD
<b>Thermal Conductivity</b>	EN12664	0,14 W/mK
<b>Thermal Resistance R-Value</b>		.11 (m2KW)
<b>Biological Durability</b>	EN350-2	Class 1
<b>CARB2</b>		Compliant