



# YDRE

Wood meets minerals with cold nuances from frost salt and sea weed. The scraped, flowing surface follows the structure giving each board a worn feeling.

## PRODUCT DESCRIPTION

|                           |  |
|---------------------------|--|
| <b>Article Number</b>     | 151NCSEK04KW240                                      |
| <b>Surface Treatment</b>  | Oil  |
| <b>Refining Treatment</b> | Bevelled 4-sided, brushed, light smoked, handscraped |
| <b>Dimensions</b>         | 2420 x 187 x 15 mm                                   |
| <b>Weight per Package</b> | 22 kg  |
| <b>Area per Package</b>   | 2.72 m <sup>2</sup>                                  |
| <b>Area Per Board</b>     | 0.453 m <sup>2</sup>                                 |

## DETAIL DESCRIPTION

All naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

## COLOUR CHANGE

Stained product - noticable color change over time.

## FACTS

|                            |                     |
|----------------------------|---------------------|
| <b>Wood Species</b>        | Oak                 |
| <b>Design</b>              | 1-strip             |
| <b>Grading</b>             | Dynamic             |
| <b>Range</b>               | Kährs Supreme       |
| <b>Collection</b>          | Småland Collection  |
| <b>Natural/Stained</b>     | Stained             |
| <b>Brinell Value</b>       | 3, 7                |
| <b>Joint</b>               | Woodloc® 5S         |
| <b>Floor heating</b>       | Yes                 |
| <b>Wear-layer material</b> | Hardwood            |
| <b>Core material</b>       | Pine/Spruce lamella |
| <b>Backside material</b>   | Veneer              |
| <b>Thickness</b>           | 15 mm               |
| <b>Installation method</b> | Floating, glue-down |
| <b>EAN Code</b>            | 7393969038997       |
| <b>Surface Colour</b>      | Mineral Grey        |

## CERTIFICATE



## TECHNICAL PROPERTIES

|  |             |                        |
|--|-------------|------------------------|
| <b>Moisture content</b>                      | EN13183     | 7%±2%                  |
| <b>Minimum Mean Density kg/m<sup>3</sup></b> |             | >500 kg/m <sup>3</sup> |
| <b>Reaction To Fire</b>                      | EN13501-1   | Dfl-s1                 |
| <b>Formaldehyde Emission</b>                 | EN717-1     | E1                     |
| <b>Content PCP</b>                           | CEN/TR14823 | ≤ 5 x 10-6n            |
| <b>Breaking Strength N/mm<sup>2</sup></b>    | EN1533      | NPD                    |
| <b>Thermal Conductivity</b>                  | EN12664     | 0,14 W/mK              |
| <b>Thermal Resistance R-Value</b>            |             | .11 (m2KW)             |
| <b>Biological Durability</b>                 | EN350-2     | Class 1                |
| <b>CARB2</b>                                 |             | Compliant              |