

## **OAK STURE**

Oak Sture is a true rustic product where the surface is handcrafted and deeply brushed to enhance the beauty and specific characteristics of each and every board. Smoked and stained to give it a muted light warm grey colour with big colour variations. Nature oil finished.

| PRODUCT DI            | PRODUCT DESCRIPTION                                  |  |  |  |
|-----------------------|--|--|--|--|
| Article<br>Number     | 151N7BEKFMKW240                                      |  |  |  |
| Surface<br>Treatment  | Oil  |  |  |  |
| Refining<br>Treatment | Bevelled 4-sided, handscraped, brushed, light smoked |  |  |  |
| Dimensions            | 2420 x 187 x 15 mm                                   |  |  |  |
| Weight per<br>Package | 22 kg  |  |  |  |
| Area per<br>Package   | 2.72 m²  |  |  |  |
| Area Per<br>Board     | 0.453 m²   |  |  |  |

## DETAIL DESCRIPTION

All naturally occuring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

## COLOUR CHANGE

Stained product - noticable color change over time.

|  | FACTS               |                     | TECHNICAL PROPERTIES       |             |             |
|--|---------------------|---------------------|----------------------------|-------------|-------------|
|  | Wood Species        | Oak                 | Moisture content           | EN13183     | 7%±2%       |
|  | Design              | 1-strip             | Minimun Mean Density kg/m³ |             | >500 kg/m³  |
|  | Grading             | Dynamic             | Reaction To Fire           | EN13501-1   | Dfl-s1      |
|  | Range               | Kährs Original      | Formaldehyde Emission      | EN717-1     | E1          |
|  | Collection          | Founders Collection | Content PCP                | CEN/TR14823 | ≤5 x 10-6n  |
|  | Natural/Stained     | Stained             | Breaking Strength Wmm²     | EN1533      | NPD         |
|  | Brinell Value       | 3, 7                | Thermal Conductivity       | EN12664     | 0,14 W/mK   |
|  | Joint               | Woodloc® 5S         | Thermal Resistance R-Value |             | .11 (m2K/W) |
|  | Roor heating        | Yes                 | Biological Durability      | EN350-2     | Class 1     |
|  | Wear-layer material | Hardwood            | CARB2                      |             | Compliant   |
|  | Core material       | Pine/Spruce lamella |                            |             |             |
|  | Thickness           | 15 mm               |                            |             |             |
|  | Installation method | Glue-down, floating |                            |             |             |
|  | EAN Code            | 7393969036054       |                            |             |             |
|  | CERTIFICATE         |                     |                            |             |             |

