



OAK DOME

Oak Dome is a stained oak floor in a warm white tone. The length of the board enhances the depth of the floor.

PRODUCT DESCRIPTION

| | |
|---------------------------|--------------------------------|
| Article Number | 37101AEKC1KW180 |
| Surface Treatment | Matt lacquer |
| Refining Treatment | Brushed, microbevelled 4-sided |
| Dimensions | 1810 x 150 x 7 mm |
| Weight per Package | 20 kg |
| Area per Package | 3.26 m ² |
| Area Per Board | 0.272 m ² |

DETAIL DESCRIPTION

Even colour with minor variations. Small sized knots in limited numbers allowed.

COLOUR CHANGE

Stained product - noticable color change over time.

FACTS

| | |
|----------------------------|---------------------|
| Wood Species | Oak |
| Design | 1-strip |
| Grading | Calm (City) |
| Range | Kährs Linnea |
| Collection | Habitat Collection |
| Natural/Stained | Stained |
| Brinell Value | 5 - 6 |
| Joint | Woodloc® |
| Floor heating | Yes |
| Wear-layer material | Hardwood |
| Core material | HDF |
| Thickness | 7 mm |
| Installation method | Floating, glue-down |
| EAN Code | 7393969106689 |

TECHNICAL PROPERTIES

| | | |
|--|-------------|------------------------|
| Moisture content | EN13183 | 7%±2% |
| Minimum Mean Density kg/m³ | | >800 kg/m ³ |
| Reaction To Fire | EN13501-1 | Cfl-s1 |
| Formaldehyde Emission | EN717-1 | E1 |
| Content PCP | CEN/TR14823 | ≤ 5 x 10-6n |
| Breaking Strength N/mm² | EN1533 | NPD |
| Thermal Conductivity | EN12664 | 0,22 W/mK |
| Thermal Resistance R-Value | | .31 (m2KW) |
| Biological Durability | EN350-2 | Class 1 |
| CARB2 | | Compliant |

CERTIFICATE

