



### Size Board

<b>LENGTH</b>	800 mm
<b>WIDTH</b>	800 mm
<b>TOTAL THICKNESS</b>	20 mm
<b>THICKNESS TOP LAYER</b>	6 mm

### Size Pack

<b>PACK LENGTH</b>	810 mm
<b>PACK WIDTH</b>	810 mm
<b>PACK THICKNESS</b>	50 mm
<b>PACK WEIGHT</b>	18 kg
<b>LAYERS/PACK</b>	2
<b>M<sup>2</sup>/PACK</b>	1.28 m <sup>2</sup>

### Size Pallet

<b>LENGTH PALLET</b>	1200 mm
<b>WIDTH PALLET</b>	800 mm
<b>HEIGHT PALLET</b>	1100 mm
<b>WEIGHT PALLET</b>	645 kg
<b>PACKS/PALLET</b>	35
<b>M<sup>2</sup>/PALLET</b>	44.8 m <sup>2</sup>

## Characteristics

### Top layer

<b>WOOD SPECIES</b>	Oak
<b>LATIN NAME</b>	Quercus Robur
<b>GRADE</b>	CLASSIC
<b>CONSTRUCTION</b>	2-layer
<b>THICKNESS TOP LAYER</b>	6 mm
<b>STRIPS</b>	1 strip
<b>CUTTING METHOD</b>	Sawn veneer
<b>BEVEL</b>	Distressed bevel (0,50 mm) to short and long sides
<b>COLOUR FINISH</b>	Smoked Unfinished
<b>SURFACE STRUCTURE</b>	Brushed

### Composition of the support

<b>SUPPORT TYPE</b>	Multiplex support
<b>WOOD SPECIES SUPPORT</b>	Mixed Light Hardwood
<b>SUPPORT CONSTRUCTION</b>	Multiplex (9 layers)
<b>TOTAL THICKNESS SUPPORT</b>	14 mm
<b>ADHESION</b>	Crosswise (Casco)

## Installation

### SYSTEM

Tongue and groove system



### APPLICATIONS

Light household use  
Moderate commercial use  
Normal commercial use  
Normal household use  
Intensive commercial use

### UNDERFLOOR HEATING

Yes

### RESANDABLE

The thickness of the upper layer allows resanding the floor, but this may influence the floor structure.

**Certification**

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

**Technical specifications**

- Hardness: N / mm<sup>2</sup> (Birnell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)